



AIR FILTER TESTING LABORATORIES, INC.

4632 Old LaGrange Road • Crestwood, Kentucky 40014

ASHRAE AIR FILTER TEST STANDARD 52-76
STATICALLY TESTED DEVICES

DEVICE TESTED

TEST REQUESTED BY CUMULUS FIBRES, INC.
MANUFACTURER CUMULUS FIBRES, INC.
PRODUCT NAME MEDIA PAD

REPORT NO. 6601
TEST NO. 1
SHEET NO. 1

HOW LABORATORY PROCURED TEST SAMPLE FURNISHED BY MANUFACTURER
MODEL NO. 100BWOT 77 DIMENSIONS 24 in. H 24 in. W 1 in. D

RATED PERFORMANCE DATA FROM MANUFACTURERS CATALOG NO.			DATED
AIR FLOW CAPACITY			
INITIAL RESISTANCE			
FINAL RESISTANCE			
INITIAL ATMOSPHERIC DUST SPOT EFFICIENCY			
AVERAGE ATMOSPHERIC DUST SPOT EFFICIENCY			
AVERAGE SYNTHETIC DUST WEIGHT ARRESTANCE			
ASHRAE DUST HOLDING CAPACITY			


TEST RESULTS

TEST AIR FLOW RATE	<u>1200 CFM</u>	<u>300</u>							
INITIAL RESISTANCE		<u>0.20</u>							
FINAL RESISTANCE									
INITIAL ATMOSPHERIC DUST SPOT EFFICIENCY									
AVERAGE ATMOSPHERIC DUST SPOT EFFICIENCY									
AVERAGE SYNTHETIC DUST WEIGHT ARRESTANCE									
ASHRAE DUST HOLDING CAPACITY									

TEST SECTION DUCT SIZE 24 in. x 24 in. DUST FEEDING RATE 2.08M/1000 CF
SEE BACK SIDE (PAGE 1A) FOR PERFORMANCE CURVES

PHYSICAL DESCRIPTION

FACE DIMENSIONS 24 in. x 24 in.
DEPTH 1 in. Nom.
MEDIA AREA 4 Ft.²
TYPE MEDIA NONWOVEN SYNTHETIC
TYPE & AMOUNT ADHESIVE TACKIFIED



DATE 4-22-1992 TEST SUPERVISOR J.P.S. ENGINEERING APPROVAL David J. Murphy Jr.



AIR FILTER TESTING LABORATORIES, INC.

4632 Old LaGrange Road • Crestwood, Kentucky 40014

ASHRAE STANDARD 52-76 AIR FILTER PERFORMANCE CURVES

STATICALLY
TESTED
DEVICES

REPORT NO. 6601

TEST NO. 1

SHEET NO. 2

DATE

4-22-1992


TEST SUPERVISOR

J.P.S.

ENGINEERING

APPROVAL


David J. Murphy Jr.



RESISTANCE - INCHES WATER GAGE

CLEAN DEVICE


AIRFLOW RATE VS. RESISTANCE



DUST FED VS. RESISTANCE

DUST INCREMENT - 30 GMS. ASHRAE

RESISTANCE - INCHES WATER GAGE





AIR FILTER TESTING LABORATORIES, INC.

4632 Old LaGrange Road • Crestwood, Kentucky 40014

ASHRAE STANDARD 52-76
AIR FILTER PERFORMANCE CURVES

STATICALLY
TESTED
DEVICES

REPORT NO. 6601


TEST NO. 1

SHEET NO. 3

DUST FED VS. ARRESTANCE

DUST INCREMENT - 30 OMS, ASHRAE

ASHRAE SYNTHETIC DUST WEIGHT ARRESTANCE - PERCENT



DATE

4-22-1992

TEST SUPERVISOR

J.P.S.

ENGINEERING

APPROVAL

David J. Murphy Jr.

